
DATA SHEET




Pro Hardcourt

Standard Colours



The colour of the applied coating may differ from the above representation. Contact our Technical Service Department if an accurate sample is required. Special colours are also available on request.

Court Design Sports-Cote[™] Pro Hardcourt



Description

Sports-Cote[™] Pro Hardcourt is an acrylic sports surface designed to give optimum and grip and excellent play characteristics.

The **Sports-Cote[™] Pro Hardcourt** system comprises an acrylic re-surfacer and three coloured acrylic layers.



Uses

Sports-Cote[™] Pro Hardcourt is used as a playing surface for tennis, netball and multi-use games areas (MUGA's).

Model Specification

- Product: **Sports-Cote[™] Pro Hardcourt**
- ITF Classification: 1, 2, 3, 4 or 5

• Finish: Extra Texture (tennis) and Full Texture (netball)

- Colour:
- Substrate: Supplier's Instructions
- Application: Supplier's Instructions
- Supplier: Sports Coatings Limited
- Contact: Technical Service Department 01440 766366

Substrate and Preparatory Work

All loosely adhered debris must be removed by vacuuming, blowing or sweeping prior to the application of **Sports-Cote[™] Pro Hardcourt**. Any firmly adhered contamination should be removed by low pressure power washing.

Application

Sports-CoteTM Pro Hardcourt Acrylic top should be applied in three coats - two wear layers and a top coat.

The wear layers should be applied with a 600-1200mm flat blade rubber squeegee.

The first layer is applied at right angles to the playing net. Subsequent coats are applied parallel to the playing net.

The first two coats should be checked for high spots and imperfections which should be removed and sanded either by hand or with an STR type rotary sanding machine.

Do not apply when the temperature is over 50°C or below 10°C. For temperatures outside this range please consult the manufacturer.

Allow to cure for between 24 and 72 hours depending on ambient temperature before use.

Note: When applying to a rough or textured surface a Tarmac re-surfacer layer should be applied.

Sports-Cote[™] Pro Hardcourt Acrylic Tarmac re-surfacer

DATA SHEET





Pro Hardcourt

is mixed with 110 mesh kiln-dried sand at a ratio of 1:1-1.25. The application viscosity should be adjusted by the addition of clean potable water.

Sports-Cote[™] Pro Hardcourt Acrylic Tarmac re-surfacer should mixed with the appropriate size and quantity of dried sand, and applied with a 600-1200mm flat blade rubber squeegee. This should be allowed to dry before the application of subsequent layers.

Application Conditions

Sports-Cote[™] Pro Hardcourt should only be applied in fine, dry weather and when substrate temperature is higher than 5°C and likely to remain so for 6-7 hours after this. Substrate temperatures higher than 30°C should also be avoided.

Note: situations where frost may occur within 24 hours of painting must be avoided.

Packaging

Sports-Cote[™] Pro Hardcourt Acrylic: 20 litre units

Coverage

Coverage is dependant on the surface texture and mix ratio used.

1 st wear layer:	0.15-0.2 litres/m ²
2 nd wear layer:	0.15-0.2 litres/m ²
Top Coat:	0.15-0.2 litres/m ²

Note: coverage will vary depending on substrate porosity, application temperature and technique.

Technical Information

Touch dry time:2-3 hours at 20°CFull cure:72 hours approx. at 20°CSlip resistance:Meets the "wet" and "dry"requirements of the ITF (60)andAENA (75).Shelf Life

Sports-Cote[™] Pro Hardcourt components have a shelf life of approximately 12 months in original, unopened packaging.

Storage

Store above 5°C in an environment safe from frost.

Aftercare and Maintenance

Detailed guidance on the maintenance of painted courts may be found in SAPCA's Code of Practice for the Maintenance of Synthetic Sports Surfaces (www.sapca.org.uk).

Life Expectancy

If the sports surface is used in accordance with its intended purpose **Sports-Cote[™] Pro Hardcourt** will give acceptable performance for between 3 and 5 years. However, certain factors will influence the performance of the coating and may well result in premature wear. Detailed guidance on the factors can be found in SAPCA's Code of Practice for the Maintenance of Synthetic Sports Surfaces (www.sapca.org.uk).

Health and Safety

For detailed information please refer to the current Material Safety Data Sheet.

Further Information

To ensure you are specifying or applying a fit for purpose coating please contact our Technical Services Department.





Hawthorn House, Helions Bumpstead Road, Haverhill, Suffolk CB9 7AA, England Tel: +44 (0)1440 766366 Fax: +44 (0)1440 768897 Email: admin@sportscoatings.com Web: www.sportscoatings.com

Sports Coatings Ltd

